

SILIRUB N

Revision: 1/04/2024

Page 1 of 2

Technical Data

Basis	Polysiloxane
Consistency	Stable paste
Curing system	Moisture curing
Skin formation* (23°C/50% R.H.)	Ca. 6 min
Curing speed* (23°C/50% R.H.)	Ca. 2mm/24h
Hardness**	Ca. 25 ± 5 Shore A
Density	Ca. 1,00 g/ml (transp) Ca. 1,22 g/ml (colors)
Elastic recovery (ISO 7389)**	>80%
Maximum allowed distortion (ISO 11600)	20%
Max. tension (ISO 37)**	Ca. 1,05 N/mm ²
Elasticity modulus 100% (ISO 37)**	Ca. 0,30 N/mm ²
Elongation at break (ISO 37)**	Ca. 700%
Temperature resistance**	-60°C → 120°C
Application temperature	5°C → 35°C

*These values may vary depending on environmental factors such as temperature, moisture and the type of substrate.

**This information relates to fully cured products.

Description:

Silirub N is a high-quality, neutral, elastic one-component silicone based joint sealant.

Properties:

- Very easy to apply
- Permanently elastic after curing
- Very good adhesion on many materials
- UV-resistant
- Very good resistance to ageing
- Not paintable
- Not suitable for natural stone
- MEKO free

Packaging:

Colour: transparent, white, grey, black, brown and many others

Packaging: 300ml cartridge, 400ml foil bag, 600ml foil bag

Applications:

- All usual building joints with high movement
- Glazing and joint works
- Expansion joints between many different construction materials
- Sealing between PVC, treated wooden and metal profiles and glass

Shelf Life and Storage:

12 months in unopened packaging in a cool and dry storage place at temperatures between +5°C and +25°C.

Health and Safety Recommendations:

Take the usual labour hygiene into account. Consult label and material safety data sheet for more information. Dangerous! Respect the precautions for use.

Substrates:

Substrates: all usual building substrates
Nature: rigid, clean, dry, free of dust and grease.
Surface preparation: Porous surfaces should be primed with Primer 150. Prepare non porous surfaces with a Soudal activator or cleaner (see Technical Data Sheet). We recommend a preliminary adhesion and compatibility test on every surface. Not suitable for PE, PP, PTFE (eg Teflon®), bituminous substrates, copper or copper-containing materials such as bronze and brass.

Application Method:

Apply the product by means of a manual, battery or pneumatic - caulking gun. Apply Silirub N evenly without air inclusions into the joint. Smoothen the joint with a spatula with the help of finishing solution. Avoid that soapy solution comes between the joint edges and

Remark: The directives contained in this documentation are the result of our experiments and of our experience and have been submitted in good faith. Because of the diversity of the materials and substrates and the great number of possible applications which are out of our control, we cannot accept any responsibility for the results obtained. In every case it is recommended to carry out preliminary experiments.

Soudal India Pvt. Ltd.

Plot No. 200, Sec. 4, Phase - II, Growth Centre, Bawal, Dist. Rewari, Haryana - 123501 (India)

info@soudal.in | www.soudal.in | +91 8010-114-114

SILIRUB N

Revision: 1/04/2024**Page 2 of 2**

sealant (to prevent adhesion loss).

Application method: With a manual, pneumatic or accu caulking gun.

Cleaning: Clean with White Spirit or Soudal Surface Cleaner immediately after use (before curing).

Finishing: With a soapy solution or Soudal Finishing Solution before skinning.

Repair: With the same material.

Joint Dimension:

Min. width for joints: 5 mm

Max. width for joints: 30 mm

Min. depth for joints: 5 mm

Recommendation sealing jobs:

joint width = 2x joint depth.

Three-point adhesion should be avoided at all time. Too small joint dimensions can have the effect that the silicone is pulled off because of too large movements.

Remarks:

- Do not use on natural stones like marble, granite etc. (staining). Use Soudal Silirub MA or Soudaseal 212 CS for this application.
- Direct contact with the secondary sealing of insulating glass units (insulation) and the PVB-film of safety glass must be avoided.
- Because of the diversity we recommend to do adhesion tests on aluminum lackers, textured coating and PVC before application.
- In an acid environment or in a dark room, a white sealant can slightly turn yellow under the influence of sunlight it will turn back to its initial colour.
- When finished with a finishing solution or soapy solution, make sure that the surfaces are not touched by this solution. This will cause the sealant not to adhere to that surface. Therefore we recommend to only dip the finishing tool in this solution.
- Do not use in applications where continuous water

immersion is possible.

- Do not use on polycarbonate. Use Silirub PC instead.
- When using different reactive joint sealants, the first joint sealant must be completely hardened before the next one is applied.
- Contact with bitumen, tar or other plasticizer releasing materials such as EPDM, neoprene, butyl, etc. is to be avoided since it can give rise to discolouration and loss of adhesion.

Environmental Clauses:

Leed regulation:

Silirub N conforms to the requirements of LEED. Low –Emitting Materials: Adhesives and Sealants. SCAQMD rule 1168. Complies with USGBC LEED 2009 Credit 4.1: Low-Emitting Materials – Adhesives & Sealants concerning the VOC content.

Liability:

The content of this technical data sheet is the result of tests, monitoring and experience. It is general in nature and does not constitute any liability. It is the responsibility of the user to determine by his own tests whether the product is suitable for the application.

Remark: The directives contained in this documentation are the result of our experiments and of our experience and have been submitted in good faith. Because of the diversity of the materials and substrates and the great number of possible applications which are out of our control, we cannot accept any responsibility for the results obtained. In every case it is recommended to carry out preliminary experiments.