

COSEAL STYLE 2708

NON-ASBESTOS JOINTING SHEET



Basis

High-performance gasket material engineered with aramid fiber, organic fiber, and NBR binder for superior flexibility and chemical resistance.

Application

60

20

1

100

150

50

Fluid Pressure (Bar)

Ideal for medium-stress applications with temperature and pressure fluctuations, including:

- 1 Petroleum products: Oils, fuels, lubricants, hydrocarbons
- 2 Industrial fluids: Alcohols, cooling liquids, steam, water
- 3 Chemical media: Most diluted acids and alkalis
- 4 Gas systems: Various industrial gases

50 40 30 2.

200

Temperature (°C)

250

300

350

400

Area of Application

- Suitable Suitable when chemical compatibility is verified
- 2. **Conditionally Suitable** Consultation recommended for marginal applications
- 3. **Not Recommended** Installation prohibited without comprehensive technical assessment

| Parameter | Standard | Coseal 2708 | Units |
|--|-------------|-------------|---------|
| Max. Peak Temperature | | 400 | °C |
| Max Operating Temperature | | 270 | °C |
| Max. Operating Pressure | | 100 | bar |
| Density | ASTM F 1315 | 1.70-1.9 | g/cm³ |
| Compressibility | ASTM F 36 J | 7-17.0 | % |
| Recovery | ASTM F 36 J | ≥ 45.0 | % |
| Tensile Strength | ASTM F 152 | ≥ 10.0 | N/mm² |
| Gas Permeability | BS 7531 | ≤ 1.0 | ml/min. |
| ASTM oil no.3 (5h, 150°C) | ASTM F 146 | | |
| Thickness Increase | | ≤ 5.0 | % |
| Weight Increase | | ≤ 10.0 | % |
| Fuel B (5h, 23°C) | ASTM F 146 | | |
| Thickness Increase | | ≤ 6.0 | % |
| Weight Increase | | ≤ 13.0 | % |
| Water (5h, 100°C) | ASTM F 146 | | |
| Thickness Increase | | ≤ 5.0 | % |
| Weight Increase | | ≤ 11.0 | % |
| Stress Relaxation (16h X 175°C 2.00mm) | DIN 52913 | ≥ 18.0 | MPA |
| Colour | | Dark Blue | |

